

Review

Green Synthesis of Ag₂O Nanoparticles by Using Plant Extract: A Review

Kajeen Sarbast Mustafa ¹, Ahmed Fattah Abdulrahman ^{2, 3, *}

¹ Department of Physics, College of Science, University of Zakho, Zakho, Kurdistan Region, 42002, Iraq.

² Department of Energy Engineering, Technical College of Engineering, Duhok Polytechnique University, Duhok, Kurdistan Region, Iraq. ²; ahmed.abdulrahman@dpu.edu.krd

³ Department of Medical Laboratory Technology, Technical Institute of Amedi, Duhok Polytechnic University, Duhok, Kurdistan Region, 42008, Iraq.

* Correspondence: ahmed.abdulrahman@dpu.edu.krd

Abstract

Studying materials at the nanoscale is the focus of the quickly expanding science of nanotechnology. Conventional techniques for producing metal nanoparticles need sophisticated equipment or costly ingredients. Moreover, the techniques may not be environmentally safe. Therefore, while synthesizing nanoparticles, "green" techniques that are simple to use, reasonably priced, environmentally benign, and convenient are always used. Using biological sources to produce nanoparticles is a novel process known as "green synthesis." Its large-scale, ecologically friendly, and competitively cost production alternatives are contributing to its growing popularity. Green methods of synthesizing nanomaterials involve the usage of biological natural systems. This review highlights the development for environmentally favorable to traditional methods for nanoparticle production. Complete the usage of energy-low processes also naturally occurring starting materials, green synthesis provides an equally effective, if not more effective, sustainable method of fabricating nanomaterials than normal synthesis. There have been recent reports of successful attempts to synthesis various nanoparticle systems by using active compounds found in naturally occurring biological systems, including bacteria, algae, yeast, and fungus. Therefore, employing green synthesis in large-scale manufacturing and research offers a practical way to overcome the drawbacks of conventional synthesis techniques.

Keywords: Silver Oxide NPs; green synthesis, nanomaterials; plant extract; fungi.

1. Introduction

Nanotechnology is a quickly developing area of investigation that focuses on producing nanomaterials and nanoparticles (NPs) for use in a diversity of applications, as well as biomedicine, food technology, sensing, and electrochemistry [1–3]. Nanoparticles (NPs) are solid, atomic or molecular sized smaller particles than 100 nm in size, with unique physical characteristics in relation to the size of molecules-bulk. Their size and form vary [4]. Among other benefits, metal oxide nanoparticles besides metal have involved lots of consideration in technology and science owing to their excellent dispersion in solutions and volume ratio of high surface. [5]. These are reasons why metal oxide nanoparticles and metal exhibit enhanced capabilities of antibacterial [6].

These days, industrially produced goods like electronics, textiles, and cosmetics frequently include synthetic or modified nanoparticles (NPs). Furthermore, because bacteria are becoming increasingly resistant to antibiotics, new medications need to be created as either stand-alone Nanoparticles otherwise in combination with current antibiotics

in the direction of have a positive effect of synergistic. Because of this, NPs are currently frequently used in many different medical fields [7]. These days, molecular imaging with NPs is used toward produce resolved images highly aimed at diagnosis. Moreover, contrast chemicals remain filled onto NPs to atherosclerosis diagnose and tumors [8].

Moreover, meanwhile the approved of FDA the primary nanotherapeutic in 1990, It's been worldwide encouragement to create a range of drugs based on nanotechnology [9]. In order to increase the efficiency of Nanoparticles synthesis, A change of chemical and physical techniques, together with milling and chemical reduction, were used in the start of the twentieth century [10]. Though, because these methods of traditional need costly besides chemicals dangerous, they cannot remain considered environmentally friendly operations [11]. Considering this, scientists be situated currently very involved trendy of biogenic method of synthesizing metal oxide and metal nanoparticles (NPs), which uses microorganisms and aqueous plant extract and is environmentally safe, stable, therapeutically adaptive, and economical [12]. Consequently, nanoparticles for synthesis utilizing bioinspired knowledge have gained significant traction in the fields of nanotechnology and nanoscience.

Microbes and plant extract have been conditioned create a diversity of metal oxide and metal nanoparticles [13]. Typically, plant biomass is utilized to create nanoparticles, but because of its vast availability, renewable nature, and environmental friendliness, our group and others are also interested in by means of it in place of a catalyst in synthesis of chemical also biodiesel production [14]. Nanoparticles of Silver, also recognized as metal nanoparticles, are gaining increased attention from the scientific community owing to their range extensive of fields of applications such as cell parasitology biology, pharmacology, food technology, chemistry, and microbiology [15]. arrangement for Nanoparticles of silver influences their chemical and physical properties. Ag_2O consume generally been produced by means of a diversity of techniques, such as the microwave-assisted combustion method, the method technique, thermal decomposition, hydrothermal, sol-gel chemical vapor deposition, etc [16].

Silver nanoparticles' antimicrobial qualities (AgNPs), which be situated produced lately via biogenic synthesis by the usage of plant extract and microorganisms in place of reducing agents, have been extensively studied. Many biomolecules, such as aldehydes, flavonoids, ketones, carboxylic acids, tannins, polyphenols, also protein found in extracts of plant, oxidize Ag^+ in the direction of Ag^0 to form AgNPs [17]. One popular and simple analytical technique for monitoring AgNP production is UV-visible spectroscopy. When electrons conducting trendy a nanoparticle of metal outmost interact orbital through a field of electromagnetic and collectively vibrate trendy resonance by means of specific wavelengths, the known phenomenon as (SPR) surface plasmon resonance takes place. When SPR remains activated, AgNPs liquified trendy a solution colloidal change in absorbance and color. It is common practice to utilize peaks of SPR at 435 nm in the direction of validate that AgNPs are the result of converting silver nitrate.[18]. typically, Spherical NPs demonstration individual one band SPR in their absorbance spectra, whereas particles of anisotropic may display more or two bands of SPR. When a peak trendy the spectra of UV-Vis is absent between 335 and 560 nm, it might indicate that there isn't any NP aggregation [19].

2. Synthesis Methods of silver nanoparticle

There are numerous methods for producing silver nanoparticles., including biological, physical and chemical, synthesis as shown in the Figure 1. It is crucial to keep in mind that every strategy has advantages and disadvantages [20]. The organism reduces Ag^+ on the way to produce Ag^0 through the biological synthesis of silver nanoparticles, substitute by means of a reducing, capping, or stabilizing agent. Because of their inexpensive, large yields, besides low toxicity to humans and the biological, environment technologies created on products natural produced as of plant besides microbial sources have become more and more popular in recent years. The subsequent sections provide an overview of several methods used to create silver nanoparticles [21].




Figure 1. techniques for synthesizing nanoparticles [22].

2.1 Physical Methods

The processes of evaporation and condensation are crucial to the physical synthesis of AgNPs. For vapor cooling to proceed at the right rate, there must be a temperature gradient. Solvent contamination has been ruled out since the physical method achieves a flawless uniform distribution of particle size without the use of any solvent [23].

The synthesis of high concentrations of nanoscale nanoparticles can readily attain the minimum inhibitory concentration in toxicity tests. Additionally, metallic particles are laser-ablated to create AgNPs. The nonexistence of reagents chemical trending solutions makes the laser ablation approach superior to conventional processes for producing metal colloids. Consequently, this method may be used to generate clean and uncontaminated metal colloids for use in other applications [24]. Physical synthesis may be used to create nanoparticles of an extensive materials of change, including PbS, Au, besides Au. synthesis of AgNPs by means of a furnace tube consumes numerous drawbacks, including the need for more area, elevated power, an abrupt rise in the external temperature, etc.

The AgNPs generated by laser ablation are greatly influenced by the effective liquid medium, wavelength of laser, laser pulse duration, laser fluence, and time ablation duration. AgNPs created by laser ablation have a direct relationship between their particle size and laser fluence, and their ejection requires minimal power [25]. However, shape, size, also form of AgNPs are essentially determined via the contact of laser light streaming. Surfactant coatings also prevent laser ablation from producing nanoparticles. The nanoparticles size formed reductions with increasing concentration of surfactant compared to decreasing surfactant concentration. Among the advantages of ablation laser over other conventional techniques aimed at producing colloids metal is the absence for additives chemical in the solutions. Consequently, procedure can produce pure colloids, which are advantageous for further applications [26].

2.1.1 Laser ablation method

This technique involves aiming a laser beam at a silver or metallic plate that has been distributed throughout a liquid as shown in the Figure 2. The beam laser remains absorbed via plate metal, creating a heated plasma with a high concentration of silver particles. [27]. When the surrounding region cools and the temperature drops due to the liquid medium, silver nanoparticles start to form. The efficiency ablation besides the kind of silver nanoparticles formed are dependent on a number of variables, including the effective liquid medium (containing or lacking surfactants), the wavelength laser that impinges on target of metallic, the length of pulses laser (in the femto-, pico-, and nanosecond regimes), laser fluency, also duration for ablation time . [28]. The core advantage of both processes is no stabilizers, chemicals, or reducers are needed, thus the pure silver nanoparticles they produce don't need to be purified beforehand. Their high cost and exorbitant energy use are, however, their biggest disadvantages. These drawbacks prompted the development of a number of methods that, although being grounded in the physical approach, overcome these

limitations. These tried-and-true techniques are comparable to using ceramic heaters, which use less energy and continually supply heat when there is a noticeable temperature differential nearby [28]. Heat breakdown is the second method that is used to produce solid silver nanoparticles. This method, which works by complexing silver with oleate ions, yields 10 nm-sized silver nanoparticles. The arch dispersion process, which produces nanoparticles of silver smaller than 10 nm in size also is from now extremely effective, also solved the previously described limits. It is the process by which silver nanoparticles develop trendy water deionized deprived of the need for surface-active agent [29].




Figure 2. Diagrams showing the mechanism used to create particles during laser ablation [30].

2.1.2 Sputtering

Using a top-down approach, high-energy particles, such argon ions, are used to bombard a solid surface. This process erodes the surface and forms atoms by way of a consequence of the impact between the solid surface and energetic particles as shown in the Figure 3 [31]. How Sputtering Occurs: Sputtering may be clearly understood in terms of two theoretical theories: (i) According to the thermal vaporization theory, the heat produced by high-energy particles impacting a solid surface cause it to evaporate. (ii) The momentum-transfer theory suggests that atoms on solid surfaces may absorb the kinetic and/or momentum of high-energy particles. One of the element's influencing sputtering is the energy of the ions or particles being blasted. (iii) The type of target surface. (iv) The angle of reflection for particle incident. (v) Crystal structure of solid surfaces. Types of sputtering include: Basically, there are three kinds: (i) DC diode sputtering. (ii) Radio frequency sputtering. (iii) Magnetron sputtering. P. Ayyub et al. investigated synthesis for metal oxide and metal nanoparticles for Ag, Cu, ZnO, TiO₂, and γ -Al₂O₃. Researchers found that the temperature of the substrate, the sputtering power, also kind, flow, and pressure rate for sputtering gas all had an impact on the mean crystallographic orientation and size particle [32].




Figure 3. Diagrammatic representation of the magnetron sputtering process used to create nanoparticles [31].

2.2 Chemical Methods

The most popular technique for producing colloidal, stable AgNP scatterings trendy organic or water thinners is reduction of chemical. The most commonly utilized reductant is citric acid. To produce nanoscale colloidal silver ions in an aqueous solution, silver is reduced. Any stable colloidal dispersion's surface can be stabilized by adding dodecanethiol, which adsorbs to create a protective coating [33]. It has the ability to prevent crystallization and clumping in the system. Tiny changes to the polymers result in significant differences in AgNPs' morphology, size, self-assembly, polydispersibility index, and zeta potential (stability) [34]. glycol Two derivatives, polyethylene glycol (PEG) and (PVP) polyvinyl pyrrolidone, are frequently used as inputs in the manufacture of AgNPs and AuNPs. Polyacrylamide is used as a stabilizing and reducing agent trendy production of AgNPs. Functional group-containing surfactants, such by way of amines, thioils, also acids, are necessary for the stability of colloidal dispersion, which prevents crystal formation, agglomeration, and coalesces. These days, AuNPs made using the modified tollens approach are made with saccharides, silver hydrosols, and reducing agents. The resulting AgNPs are 20–50 nm and 50–200 nm in size, respectively [35].

2.2.1 The polyol method

The figure 4 shows the technique of the Polyol which is a process of chemical used to make nanoparticles. In this process, a liquid of non-aqueous called polyol remains employed in place of a reducing and solvent agent. The liquids nonaqueous in this method reduce surface oxidation and aggregation, which is one advantage. The nanoparticles have better control over their size, shape, and texture thanks to this technique. Another method for producing vast amounts of nanoparticles is the polyol process [36]. The process of polyol may remain seen by way of method of sol-gel for oxide generation if it is agreed available at a slightly higher temperature through tight control over formation particle. Numerous studies have examined the production of sub-micrometer oxide particles, including Ag_2O , TiO_2 , CoTiO_3 , SnO_2 , Mn_3O_4 , Y_2O_3 , ZnO , PbO , and V_xO_y . [37]. Owing to reducing power its strong, high boiling point, and high dielectric constant, glycol ethylene is the solvent maximum frequently utilized trendy polyol approach to produce nanoparticles of metal oxide. Furthermore, metal glycolate is created by crosslinking ethylene glycol with metal ions, which encourages oligomerization. After being calcined in air, by way of-synthesized precursors glycolate may well be able to maintain their original structure, giving rise to their more often used metal oxide offspring [38].




Figure 4. Diagram showing the polyol method's experimentation process[39].

2.2.2 Electrochemical synthesis

synthesis of Electrochemical is a process of forming compounds of chemical within a cell electrochemical. The core benefits of synthesis over electrochemical for chemical conventional reactions are its ability to accurately regulate the required voltage also discard the wasteful possibly half-reaction alternative. Recently, there consumes been lots attention in studies on the electrochemical synthesis for nanoparticles of silver.[29]. The metallic anode was dissolved in an aprotic liquid as the basis for the electrochemical process. Nanoparticles of Silver by a diameter of 2 in the direction of 7 nm were created by electrolyzing anodically soluble silver ions in acetonitrile with tetrabutylammonium.

The size particle remained attained via variable of current density. Using a variety for electrode counter types, the effects parameters of dissimilar electrochemical arranged final size particle were examined. The spectra UV-Vis exhibited the existence of the different two clusters of silver .[40] Dobre et al. also described the "sacrificial anode" method, an electrochemical technique for creating colloidal silver solutions. In this process, a handmade alternating polarity current pulse generator and a stirrer were used. poly (PVP) and Sodium lauryl sulfate (Na-LS) were employed as co- and stabilizers, respectively. Synthetically produced Ag spherical particles with a size distribution of around 10–55 nm was present. Ag nanoparticles may be identified using the band absorption at 420 nm trendy the spectra UV/Vis.

Zeta potential measurements in the range of -17 to -35 mV indicated the existence of stabilizer-covered particles with low aggregation dynamics [41]. The production electrochemical of nanoparticles for silver in aqueous (vinyl alcohol) poly (PVA) solution has been the subject of more investigation. well-known synthetic PVA polymer that has high mechanical qualities and degrades biologically. It is also nontoxic, soluble in water, and biocompatible. Ten minutes of continuous synthesis were showed by a current density of 25 mA cm⁻². A mean diameter of 15 ± 9 nm nanoparticles of silver was produced. More research has been done on the electrochemical technique that produces long-lived silver nanoparticles and silver powder in aqueous solutions. The formed silver nanoparticles, which reached in size as of 2 in the direction of 20 nm, were stable for more than seven years. Agglomerated silver nanoparticles smaller than 40 nm were seen to form silver crystals arranged the cathode surface [42]. The process of producing NH₃ on a VN/(titanium mesh) (VN/TM) catalyst using the Mars-van Krevelen mechanism in an HCl cell is shown in the Figure 5 [39].




Figure 5. Diagram illustrating the process of producing NH₃ on a VN/(titanium mesh) (VN/TM) catalyst using the Mars-van Krevelen mechanism in an HCl cell. Taken from [39].

2.3 Biological Methods

Biological AgNPs synthesis can be achieved by novel techniques such as biotechnology. Because of their greater surface area, magnetic nanoparticles can also cure heightened microbial resistance to a variety of drugs and antibiotics [43]. They also have strong antibacterial effect. Green chemistry, the rapidly developing method of producing AgNPs without any adverse side effects, is made possible by the utilization of naturally occurring stabilizing, reducing, and capping compounds [43]. Herbs have been effectively demonstrated to reduce metal ions when used in conjunction with certain proteins, germs, bacteria, fungus, and enzymes in biological synthesis [44].

3. Types of Green Syntheses

Top-bottom and bottom-top are the two methods used to create nanoparticles. Among the bottom-top strategies are the biological (Green) syntheses. These techniques include the creation of nanoparticles by (microorganisms and plants). There are three stages to biosynthesis for plant-mediated nanoparticles: the stabilization, reduction, and growth phases [45]. When plant metabolites-biomolecules with the ability to undergo reduction-interact with one another, the ions metal are unconventional beginning for precursors salt during the most crucial phase, called the period of decrease. The transition of metal ions from divalent or mono- oxidation states to ones zero-valent results in the reduced metal atoms for nucleation. [46].

In the course of development, the separated atoms of metal subsequently combine in the direction of generate nanoparticles of metal; nevertheless, further reduction of biological for ions metal occurs. The phase growth produces the increased stability thermodynamic of the produced NPs, even if excessive nucleation might cause the nanoparticles to agglomerate and alter form. The phase of final in the creation of NPs remains stability. The nanoparticles in due course assume their maximum stable and potent form once they are covered in plant metabolites. Because this procedure is friendly environmentally also does not necessitate usage of dangerous chemicals, it has been used by many researchers [47]. The biological module lowers the total cost of the synthesis process by acting both by reducing and by capping representative.

While high pressure and high energy external experimental conditions are no longer required, the foremost disadvantage of applying synthesis aimed at bacteria NPs it is a slower process than using extract of plant. In addition to this, separation techniques and superior culture studies are required. fundamentals of energy-saving processes. In the large-scale production of nanoparticles, cannister stays are employed. In addition to producing, use less energy to create a safer product [48].

3.1 Bacteria

Beneficial bacteria have its place in the direction of a huge family of organisms unicellular by wall cells nonetheless no organized nucleus or organelles. This group of organisms is helpful for producing nanomaterials in an eco-friendly manner. While certain kinds of bacteria can be extremely dangerous, the majority of bacteria are found obviously trendy the pose and body little in the direction of no damage to the person handling them. Numerous types also contain easily adaptable genetic codes and are quite easy to grow, such as *Bacillus subtilis* and *Escherichia coli*. [49]. These characteristics make using bacteria to produce nanoparticles a useful technique. Once the bacteria have aerobically grown to the density essential optical, they are joint by the precursor for nanoparticles and the medium growth containing a cell on the way to produce the nanomaterials. If the solution shows a noticeable color shift after incubation,

the material remains centrifuged by the side of a high speed ($\geq 10,000$ RPM). This spin produces nanomaterials that are suspended in the supernatant. The final shape and size for a nanoparticle are measured via the specific bacterial strains also precursors. For example, Gurunathan et al. and Sweeney et al. demonstrated how dissimilar kinds of silver, gold, and cadmium nanoparticles were synthesized and how they interacted with different biomolecules. Gurunathan et al. report that the chloauric solution and silver nitrate interacted with a proteins arranged the external of *E. coli*'s cell walls to form irregular and triangle-shaped gold and silver nanoparticle morphologies. [50].

3.2 Yeast (Live and Extract)

Yeast has only one cell organism related to bacteria that belongs to the fungus family. The species most often and historically employed to ferment carbohydrates into carbon dioxide and alcohols is *Saccharomyces cerevisiae*. This specific species is utilized to manufacture alcoholic drinks by fermentation and baking. Certain yeast species, like

Candida albicans, can cause potentially deadly bloodstream and systemic infections; these species are not all innocuous, like the ones used in baking [51]. A vast variety of nano systems that are not attainable with bacteria may be produced using yeast cells. It has been possible to create silver, gold, lead sulfide, selenium, ferrous oxide, cadmium sulfide, and antimony nanoparticles using yeast species. One can use cells living, extracts cell, or extra commonly used composites nanomaterial, such gold and silver, to develop nano systems. It was discovered by Sivaraj et al. that silver chloride nanoparticles could be produced efficiently with extracted proteins since yeast of commercial. Prior to converting commercial yeast extracts into nanoparticles, the scientists treated the extracts with precursor solutions and allowed them to ferment for a whole day. The fluid was collected by the researchers after this incubation time, and they steriley filtered it to create a solution that included just the nanoparticles.

The investigation likewise displayed that the first amine of numerous proteins concealed trendly the yeast wall cell was specifically accountable aimed at the reduction silver chloride into nanoparticles. Additionally, it has been shown that this particular nanoparticle has advantageous anti-mycobacterial properties. Kowshik et al.'s initial investigation showed how to create nanoparticles from silver-tolerant MKY-3 yeast cells.[52]. Similar to supplementary living things, yeast can make proteins consist of amino acids certain that can stabilize and decrease nanoparticles. Quinones are yeast-specific molecules that are consequent as of compounds aromatic besides are thought to help in the creation of nanoparticles. When the internal pH drops, the oxidoreductases are triggered towards reduce ions metal. Quinones can help convert simple metal ions into more ordered nanoparticles due to their potent nucleophilicity and redox characteristics [53].

3.3 Fungi

Fungi are classified as eukaryotic organisms because they secrete digestive enzymes into their surroundings, which they subsequently consume once the molecules disintegrate. This broad term refers to yeast. But the polymer long-chain also derivative glucose identified as chitin, which fortifies their walls cell, is what distinguishes them. Fungal cell walls include chitin, which can result in a range wide of nanoparticle forms, compositions, and sizes. It is possible to make mutually intracellular and extracellular nanoparticles consuming enzymes and protein residues. To begin the process of creating nanomaterials from fungus, the fungus must be extracted and allowed to grow in broth for a full 72 hours. After that, the biomass is filtered. The biomass remains raised by the precursor for nanoparticles following a thorough washing. The final solution has the nanoparticles in it after a day [53].

Verticillium is the genus that produces the fatal *Verticillium* Wilt. Mukherjee et al. discovered that *Verticillium* may produce Ag NPs on its walls cell via aqueous silver nitrate reducing [54]. Furthermore, research has demonstrated that intracellular proteins can promote the creation of nanoparticles. Ahmad et al. and Gericke et al. have demonstrated that the internal enzymes of *Verticillium luteoalbum* and *Trichothecium*, individually, produce gold nanorods and nanospheres. [55]. Extra research remains necessary towards fully explore the interesting medical and therapeutic implications of nanoparticles. Edible mushroom extracts possess anticancer capabilities and can be converted into nanoparticles with comparable characteristics, as per Phillip et al. Philip and associates [56]. discovered that fungi's amino acid residues, such cysteine, can help produce nanoparticles. Amino acids function as stabilizing and capping agents in the cell walls of fungi, much like in bacteria. According to Phillip et al., therapeutic nanoparticles are non-toxic in dissimilarity to ordinary NPs [56].

3.4 Algal Species

Algae are Seldom, which are eukaryotic, phytosynthetic organisms, categorized as plants. Water is necessary for all living forms that possess chlorophyll, whether they are single- or multicellular; but, unlike plants, they lack vascular systems, stalks, and leaves. Additionally, they may aid people in ways that involve treatments like spirulina, which has a high concentration of naturally occurring minerals. [57]. If ingested, toxic species like *Anabaena* can be lethal. Numerous types of algae have been shown to possess the ability in the direction of catalyze the nanomaterials synthesis. a tasters are totally dried, ground obsessed by a fine powder, combined by water, incubated for a whole day, and then filtered to produce nanomaterials from different algae species. [58]. After filtering, the biomass excess remains joint by the precursor nanomaterial and incubated by the side of temperature room up until the solution changes color, indicating that the nanomaterial has been produced. *Tetraselmis kochinensis*, an algae species, employs enzymes arranged the wall cell besides trendly a cytoplasm to create gold nanoparticles, just like fungus and bacteria.

All produce spherical nanoparticles, similar to those catalyzed by fungi and bacteria. Sinha et al [59]. discovered that *Pithophora oedogonia* can produce hexagonal and cubical silver nanoparticles, in addition to nanospheres. Aside from morphology, algae besides additional agent's green have comparable chemicals bioactive. Algal nanoparticles may effectively kill germs. Algal nanoparticles may be helpful at killing germs. Algae make nanoparticles containing bioactive compounds comparable to other classes, but with minor variations [60]. In algae, Polysaccharides and protein residues have the ability to both stabilize and reduce nanoparticles. One of the main advantages of employing algae is the availability of a wide variety of phytochemicals. phenols, Amino acids, saponins, carbohydrates, flavonoids, tannins, sterols, and alkaloids are altogether contemporary in *Sargassum tenerrimum* algae. Any chemical can alter the nanomaterial's size, shape, and active properties on its own once it has been purified. The development and use of algae-based nanomaterials in the future is made possible by the characterization performed by Kumar et al [61].

3.5 Plant and Plant Extract

Using food or plant leftovers to generate nanomaterials is a very innovative and ecologically beneficial green synthesis method as shown in the Figure 7. Plant or food leftovers are often processed to recover chemical components. Typically, food or plant scraps are dried, crushed up, then immersed in water hot intended for a length time before being filtered in addition kept at 4°C [62].




Figure 6. A diagrammatic illustration of reduction of ions silver by plant extract biomolecules [63].

Dependent on plant material or else plant used intended for extraction, the filtered reagent may include a variety of bioactive chemicals. Nevertheless, the creation of nanoparticles may also be related to proteins, glucosides, and polysaccharides. Plant extracts often include phenols, terpenoids, and flavonoids. The functional elements of these bioactive substances stabilize and decrease the precursors of nanoparticles [64]. By using this process of synthesizing nanoparticles, there is no need for harsh chemicals that might harm the environment or the user. Additionally, The requirement for very energy-intensive procedures is removed by extracting the bioactive compounds with merely warm water. Since harsh reagents are not needed, the common of the generated nanoparticles it could be employed in applications of biomedical. [65]. The maximum kind of prevalent for nanoparticle produced via plant material, according to relevant research, is silver nanoparticles. Reports on the production of nanoparticles have also cited copper, gold, and selenium in addition to silver. Silver nanoparticles may be produced using a wide range of plant sources whose extracts include reducing, stabilizing, and capping agents.

For instance, capping, stabilizing, and reducing agents include, among many others, tea polyphenols, *Carpesium cernuum* (a native Chinese plant), *cannabis sativa*, vegetable oil, and black currant (a native Asian also European fruit). A 2010 research by Moulton et al. found that polyphenol-rich tea leaves may be utilized to make colloidal silver nanoparticles. Their synthesis method is comparable to those previously mentioned. The researchers manufactured their silver nanoparticles by boiling, filtering, and adding silver nitrate to powder tea, it was composed of crushed besides dried leaves tea. This was established using transmission electron microscopy TEM [66].

After that, the researchers employed assays for cell survival and membrane integrity to ascertain A toxicity nanoparticles on systems of biological. A good result was that the NPs exhibited possible biocompatibility and no toxicity [66]. Extra plant common material that numerous store people trendy their cambooses be situated vegetable oil. Kumar et al. employed free radicals, which remain commonly present in paints used in houses that are complete as of specific vegetable oils, such cashew oil, to generate metallic nanoparticles in a more ecologically friendly way [67].

The researchers converted silver benzoate, a popular silver salt used trendy the assembly of nanoparticles for silver, into silver nanoparticles during the oxidative drying of oils by using obviously taking place exchange of free radical. In addition, the researchers used aldehydes and acids from the oils in place of process stabilizers and alkyd resin as a protective agent. Their reaction produced paints with added silver nanoparticles and antimicrobial qualities [67]. Another plant agent that can be used to make nanoparticles is aloe vera. Aloe vera is a common sunburn remedy these days and a key component of traditional medicines that heal a wide range of illnesses. Fardsadegh et al. Aloe vera remained used to effectively create selenium nanoparticles with antifungal and antibacterial qualities. The hydrothermal technique, which is emphasized as a typical synthesis method, was used by the Fardsadegh group.

Despite its drawbacks, this procedure is more ecologically friendly than others due of its high energy consumption [68]. Similar to the compounds found in plant leaves, the chemicals present in our favorite spices also have activity that may be used. In Indonesia, a particular variety of evergreen tree produces the fruit of the *Myristica fragrans* tree. This fruit produces common cooking spices like nutmeg and mace when dried and powdered.

Metallic nanoparticles are created when the fruit's pericarp, or non-seed component, is dried, crushed, additional in the direction of water, and cooked by cupric oxide, commonly known as silver nitrate [69]. Subsequent investigation by Sasidharan et al. revealed that the myristic fragrans' flavonoids, quecetin, and phenols were mostly responsible for the nanoparticles' stability and decline. Moreover, They discovered that the bacterial cell walls could be easily broken down by the silver nanoparticles. Furthermore, Sasidharan and colleagues discovered that the production of triazole rings was effectively enhanced by the copper nanoparticles. [69]. Subsequent investigation by Sasidharan et al. revealed that the myristic fragrans' flavonoids, quecetin, and phenols were mostly responsible for the nanoparticles' stability and decline.

They also found that the silver nanoparticles were remarkably effective in breaking down bacterial cell walls. Moreover, Sasidharan et al. found that the copper nanoparticles were a powerful catalyst for the synthesis of triazole rings. [70]. The scientists provided an illustration of how the silver nitrate found in the growing soil supplied the plant's shoot with silver in its first oxidation stage. Inside the plant, the silver particles had now shrunk to the size of nanoparticles. As soon as the nanoparticles began to form, they organized into systems that resembled nanowires [70]. Marchiol et al. report that two other living plant species that have shown capable of producing nanoparticles are red fescue (*Festuca Rubra*) and black mustard (*Brassica Juncea*). Once the plants reached their maximum size, they were subjected to 1000 parts per million of silver nitrate for an entire day. The plants at this stage took up silver nitrate and stored it in their roots and stems. Plants frequently include ascorbic, citric, phenolic, and sugars (fructose and glucose), all of which combine to stabilize and reduce the levels of silver nitrate within the plant's system. After reduction, the silver produced TEM-visible nanoparticles.[71].

4. Conclusions

Research on nanomaterials is still ongoing, and its area and applications are growing. Due to their high energy requirements and use of hazardous chemicals, traditional nanomaterial manufacturing methods including chemical vapor deposition, laser ablation, Sol-Gel, flame spray pyrolysis, ultrasound, and hydrothermal are bad for the environment. The use of these technologies is careless and foolish given the present acceleration of climate change because of their detrimental consequences on the environment. The number of organisms from which active compounds from naturally occurring biological systems may be extracted is constantly increasing. It is possible to modify the active molecules used in the synthesis of nanomaterials to create materials with precise and refined shapes, antibacterial, stabilizing, reducing, and capping properties. For specific applications, nano system synthesis may be tailored to generate micron-sized nanowires, small 0D nanoparticles, or even nanosheets. All things considered, identifying the key molecules for the environmentally safe synthesis of nanomaterials provides opportunities for additional developments and modifications of the chemical and physical characteristics of nanomaterials that benefit the scientific

community in general. Green synthesis methods are almost harm-free for the environment and the workers, and they are every bit as successful as traditional method. We believe that nanomaterials will fundamentally change how we live our daily lives.

References

1. Bera, A.; Belhaj, H. Application of Nanotechnology by Means of Nanoparticles and Nanodispersions in Oil Recovery - A Comprehensive Review. *Journal of Natural Gas Science and Engineering* **2016**, *34*, 1284–1309, doi:10.1016/j.jngse.2016.08.023.
2. Ayelén Vélez, M.; Cristina Perotti, M.; Santiago, L.; María Gennaro, A.; Hynes, E. *Bioactive Compounds Delivery Using Nanotechnology: Design and Applications in Dairy Food*; Elsevier Inc., 2016; ISBN 9780128043042.
3. Frewer, L.J.; Gupta, N.; George, S.; Fischer, A.R.H.; Giles, E.L.; Coles, D. Consumer Attitudes towards Nanotechnologies Applied to Food Production. *Trends in Food Science and Technology* **2014**, *40*, 211–225, doi:10.1016/j.tifs.2014.06.005.
4. Newfang, D.A.; Johnson, G.T.; Harbison, R.D. Nanoparticles. *Hamilton and Hardy's Industrial Toxicology: Sixth Edition* **2015**, *5*, 1025–1028, doi:10.1002/9781118834015.ch97.
5. Sebestyén, V. Renewable and Sustainable Energy Reviews: Environmental Impact Networks of Renewable Energy Power Plants. *Renewable and Sustainable Energy Reviews* **2021**, *151*, doi:10.1016/j.rser.2021.111626.
6. Bagheri, S.; Julkapli, N.M. Modified Iron Oxide Nanomaterials: Functionalization and Application. *Journal of Magnetism and Magnetic Materials* **2016**, *416*, 117–133, doi:10.1016/j.jmmm.2016.05.042.
7. Medina, C.; Santos-Martinez, M.J.; Radomski, A.; Corrigan, O.I.; Radomski, M.W. Nanoparticles: Pharmacological and Toxicological Significance. *British Journal of Pharmacology* **2007**, *150*, 552–558, doi:10.1038/sj.bjp.0707130.
8. Xu, C.; Akakuru, O.U.; Zheng, J.; Wu, A. Applications of Iron Oxide-Based Magnetic Nanoparticles in the Diagnosis and Treatment of Bacterial Infections. *Frontiers in Bioengineering and Biotechnology* **2019**, *7*, 1–15, doi:10.3389/fbioe.2019.00141.
9. Handel, A.E.; Ebers, G.C.; Ramagopalan, S. V. Epigenetics: Molecular Mechanisms and Implications for Disease. *Trends in Molecular Medicine* **2010**, *16*, 7–16, doi:10.1016/j.molmed.2009.11.003.
10. Ahmed, S.; Ahmad, M.; Swami, B.L.; Ikram, S. A Review on Plants Extract Mediated Synthesis of Silver Nanoparticles for Antimicrobial Applications: A Green Expertise. *Journal of Advanced Research* **2016**, *7*, 17–28, doi:10.1016/j.jare.2015.02.007.
11. Vijayan, S.R.; Santhiyagu, P.; Ramasamy, R.; Arivalagan, P.; Kumar, G.; Ethiraj, K.; Ramaswamy, B.R. Seaweeds: A Resource for Marine Bionanotechnology. *Enzyme and Microbial Technology* **2016**, *95*, 45–57, doi:10.1016/j.enzmictec.2016.06.009.
12. Ahmed, S.; Annu; Ikram, S.; Yudha, S. Biosynthesis of Gold Nanoparticles: A Green Approach. *Journal of Photochemistry and Photobiology B: Biology* **2016**, *161*, 141–153, doi:10.1016/j.jphotobiol.2016.04.034.
13. Saiqa Ikram, S.A. Silver Nanoparticles: One Pot Green Synthesis Using Terminalia Arjuna Extract for Biological Application. *Journal of Nanomedicine & Nanotechnology* **2015**, *06*, doi:10.4172/2157-7439.1000309.
14. Changmai, B.; Sudarsanam, P.; Rokhum, S.L. Biodiesel Production Using a Renewable Mesoporous Solid Catalyst. *Industrial Crops and Products* **2020**, *145*, 111911, doi:10.1016/j.indcrop.2019.111911.
15. Nour, S.; Baheiraei, N.; Imani, R.; Khodaei, M.; Alizadeh, A.; Rabiee, N.; Moazzeni, S.M. A Review of Accelerated Wound Healing Approaches: Biomaterial- Assisted Tissue Remodeling. *Journal of Materials Science: Materials in Medicine* **2019**, *30*, doi:10.1007/s10856-019-6319-6.
16. Pal, A.; Shah, S.; Devi, S. Microwave-Assisted Synthesis of Silver Nanoparticles Using Ethanol as a Reducing Agent. *Materials Chemistry and Physics* **2009**, *114*, 530–532, doi:10.1016/j.matchemphys.2008.11.056.
17. Güneş, F.; Shin, H.J.; Biswas, C.; Han, G.H.; Kim, E.S.; Chae, S.J.; Choi, J.Y.; Lee, Y.H. Layer-by-Layer Doping of Few-Layer Graphene Film. *ACS Nano* **2010**, *4*, 4595–4600, doi:10.1021/nn1008808.
18. Biswas, A.; Vanlalveni, C.; Adhikari, P.P.; Lalfakzuala, R.; Rokhum, L. Green Biosynthesis, Characterisation and Antimicrobial Activities of Silver Nanoparticles Using Fruit Extract of Solanum Viarum. *IET Nanobiotechnology* **2018**, *12*, 933–938, doi:10.1049/iet-nbt.2018.0050.
19. Kora, A.J.; Sashidhar, R.B.; Arunachalam, J. Gum Kondagoru (*Cochlospermum Gossypium*): A Template for the Green Synthesis and Stabilization of Silver Nanoparticles with Antibacterial Application. *Carbohydrate Polymers* **2010**, *82*, 670–679, doi:10.1016/j.carbpol.2010.05.034.
20. Raghavan, D.; Zewde, B.; Ambaye, A.; Stubbs III, J.; Raghavan, D. A Review of Stabilized Silver Nanoparticles – Synthesis, Biological Properties, Characterization, and Potential Areas of Applications. *JSM Nanotechnol Nanomed* **2016**, *4*, 1043.
21. Shanmuganathan, R.; Karuppusamy, I.; Saravanan, M.; Muthukumar, H.; Ponnuchamy, K.; Ramkumar, V.S.; Pugazhendhi, A. Synthesis of Silver Nanoparticles and Their Biomedical Applications - A Comprehensive Review. *Current Pharmaceutical Design* **2019**, *25*, 2650–2660, doi:10.2174/138161282566190708185506.

22. Goutam, S.P.; Saxena, G.; Roy, D.; Yadav, A.K.; Bharagava, R.N. *Green Synthesis of Nanoparticles and Their Applications in Water and Wastewater Treatment*; 2020; ISBN 9789811318917.

23. Kmisi, F.E.; Fissan, H.; Rellinghaus, B. Sintering and Evaporation Characteristics of Gas-Phase Synthesis of Size-Selected PbS Nanoparticles. *Materials Science and Engineering B: Solid-State Materials for Advanced Technology* **2000**, *69*, 329–334, doi:10.1016/S0921-5107(99)00298-6.

24. Magnusson, M.H.; Deppert, K.; Malm, J.; Bovin, J.; Samuelson, L. <JNanopartRes_1999_v1_n2_p243-251_Magnusson.Pdf>. **1999**, 243–251.

25. Jung, J.H.; Cheol Oh, H.; Soo Noh, H.; Ji, J.H.; Soo Kim, S. Metal Nanoparticle Generation Using a Small Ceramic Heater with a Local Heating Area. *Journal of Aerosol Science* **2006**, *37*, 1662–1670, doi:10.1016/j.jaerosci.2006.09.002.

26. Shih, C.Y.; Shugaev, M. V.; Wu, C.; Zhigilei, L. V. Generation of Subsurface Voids, Incubation Effect, and Formation of Nanoparticles in Short Pulse Laser Interactions with Bulk Metal Targets in Liquid: Molecular Dynamics Study. *Journal of Physical Chemistry C* **2017**, *121*, 16549–16567, doi:10.1021/acs.jpcc.7b02301.

27. Iravani, S.; Korbekandi, H.; Mirmohammadi, S. V.; Zolfaghari, B. Synthesis of Silver Nanoparticles: Chemical, PhysicIravani, S., Korbekandi, H., Mirmohammadi, S. V., & Zolfaghari, B. (2014). Synthesis of Silver Nanoparticles: Chemical, Physical and Biological Methods. *Research in Pharmaceutical Sciences*, *9*(6), 385–406. . *Research in pharmaceutical sciences* **2014**, *9*, 385–406.

28. Zhang, X.F.; Liu, Z.G.; Shen, W.; Gurunathan, S. Silver Nanoparticles: Synthesis, Characterization, Properties, Applications, and Therapeutic Approaches. *International Journal of Molecular Sciences* **2016**, *17*, doi:10.3390/ijms17091534.

29. Choi, J.; Kim, K.; Han, H.S.; Hwang, M.P.; Lee, K.H. Electrochemical Synthesis of Red Fluorescent Silicon Nanoparticles. *Bulletin of the Korean Chemical Society* **2014**, *35*, 35–38, doi:10.5012/bkcs.2014.35.1.35.

30. Kim, M.; Osone, S.; Kim, T.; Higashi, H.; Seto, T. Synthesis of Nanoparticles by Laser Ablation: A Review. *KONA Powder and Particle Journal* **2017**, *2017*, 80–90, doi:10.14356/kona.2017009.

31. Gahlot, A. Physical Methods of Nanoparticles Preparation-An Overview. *International Journal of Advances in Engineering and Management (IJAEM)* **2021**, *3*, 812, doi:10.35629/5252-0312812816.

32. Ayyub, P.; Chandra, R.; Taneja, P.; Sharma, A.K.; Pinto, R. Synthesis of Nanocrystalline Material by Sputtering and Laser Ablation at Low Temperatures. *Applied Physics A: Materials Science and Processing* **2001**, *73*, 67–73, doi:10.1007/s003390100833.

33. Gutiérrez, M.; Henglein, A. Formation of Colloidal Silver by “Push-Pull” Reduction of Ag⁺. *Journal of Physical Chemistry* **1993**, *97*, 11368–11370, doi:10.1021/j100146a003.

34. Oliveira, M.M.; Ugarte, D.; Zanchet, D.; Zarbin, A.J.G. Influence of Synthetic Parameters on the Size, Structure, and Stability of Dodecanethiol-Stabilized Silver Nanoparticles. *Journal of Colloid and Interface Science* **2005**, *292*, 429–435, doi:10.1016/j.jcis.2005.05.068.

35. Yin, Y.; Li, Z.Y.; Zhong, Z.; Gates, B.; Xia, Y.; Venkateswaran, S. Synthesis and Characterization of Stable Aqueous Dispersions of Silver Nanoparticles through the Tollens Process. *Journal of Materials Chemistry* **2002**, *12*, 522–527, doi:10.1039/b107469e.

36. Meshesha, B.T.; Barrabés, N.; Medina, F.; Sueiras, J.E. Polyol Mediated Synthesis & Characterization of Cu Nanoparticles : Effect of 1-Hexadecylamine as Stabilizing Agent. *Nanotechnology* **2009**, 87–91.

37. Quievry, C.; Bernard, S.; Miele, P. Polyol-Based Synthesis of Praseodymium Oxide Nanoparticles. *Nanomaterials and Nanotechnology* **2014**, *4*, 1–8, doi:10.5772/58458.

38. Hirsch, T.; Zharnikov, M.; Shaporenko, A.; Stahl, J.; Weiss, D.; Wolfbeis, O.S.; Mirsky, V.M. Size-Controlled Electrochemical Synthesis of Metal Nanoparticles on Monomolecular Templates. *Angewandte Chemie - International Edition* **2005**, *44*, 6775–6778, doi:10.1002/anie.200500912.

39. Junaidi, Triyana, K., Harsojo, & Suharyadi, E. (2016, April). Chloride ion addition for controlling shapes and properties of silver nanorods capped by polyvinyl alcohol synthesized by polyol method. In AIP Conference Proceedings (Vol. 1725, No. 1, p. 020092). AIP Publishing LLC.

40. Starowicz, M.; Stypuła, B.; Banaś, J. Electrochemical Synthesis of Silver Nanoparticles. *Electrochemistry Communications* **2006**, *8*, 227–230, doi:10.1016/j.elecom.2005.11.018.

41. Nasretdinova, G.R.; Fazleeva, R.R.; Mukhitova, R.K.; Nizameev, I.R.; Kadirov, M.K.; Ziganshina, A.Y.; Yanilkin, V. V. Electrochemical Synthesis of Silver Nanoparticles in Solution. *Electrochemistry Communications* **2015**, *50*, 69–72, doi:10.1016/j.elecom.2014.11.016.

42. Surudžić, R.; Jovanović, Ž.; Bibić, N.; Nikolić, B.; Miskovic-Stankovic, V. Electrochemical Synthesis of Silver Nanoparticles in Poly(Vinyl Alcohol) Solution. *Journal of the Serbian Chemical Society* **2013**, *78*, 2087–2098, doi:10.2298/JSC131017124S.

43. Sahayaraj, K.; Rajesh, S. Bionanoparticles: Synthesis and Antimicrobial Applications. *Science against microbial pathogens: ...* **2011**, 228–244.

44. Iravani, S. Green Synthesis of Metal Nanoparticles Using Plants. *Green Chemistry* **2011**, *13*, 2638–2650, doi:10.1039/c1gc15386b.

45. Kharissova, O. V.; Kharisov, B.I.; González, C.M.O.; Méndez, Y.P.; López, I. *Greener Synthesis of Chemical Compounds and Materials*; 2019; Vol. 6; ISBN 0000000328777.

46. Singh, N.B. Green Synthesis of Nanomaterials. *Handbook of Microbial Nanotechnology* **2022**, 225–254, doi:10.1016/B978-0-12-823426-6.00007-3.

47. Kumar, H.; Bhardwaj, K.; Kuča, K.; Kalia, A.; Nepovimova, E.; Verma, R.; Kumar, D. Flower-Based Green Synthesis of Metallic Nanoparticles: Applications beyond Fragrance. *Nanomaterials* **2020**, *10*, doi:10.3390/nano10040766.

48. Liu, T.; Baek, D.R.; Kim, J.S.; Joo, S.W.; Lim, J.K. Green Synthesis of Silver Nanoparticles with Size Distribution Depending on Reducing Species in Glycerol at Ambient PH and Temperatures. *ACS Omega* **2020**, *5*, 16246–16254, doi:10.1021/acsomega.0c02066.

49. Gurunathan, S.; Kalishwaralal, K.; Vaidyanathan, R.; Venkataraman, D.; Pandian, S.R.K.; Muniyandi, J.; Hariharan, N.; Eom, S.H. Biosynthesis, Purification and Characterization of Silver Nanoparticles Using *Escherichia Coli*. *Colloids and Surfaces B: Biointerfaces* **2009**, *74*, 328–335, doi:10.1016/j.colsurfb.2009.07.048.

50. Bahrulolum, H.; Nooraei, S.; Javanshir, N.; Tarrahimofrad, H.; Mirbagheri, V.S.; Easton, A.J.; Ahmadian, G. Green Synthesis of Metal Nanoparticles Using Microorganisms and Their Application in the Agrifood Sector. *Journal of Nanobiotechnology* **2021**, *19*, 1–26, doi:10.1186/s12951-021-00834-3.

51. Gow, N.A.R.; Yadav, B. Microbe Profile: *Candida Albicans*: A Shape-Changing, Opportunistic Pathogenic Fungus of Humans. *Microbiology (United Kingdom)* **2017**, *163*, 1145–1147, doi:10.1099/mic.0.000499.

52. Sivaraj, A.; Kumar, V.; Sunder, R.; Parthasarathy, K.; Kasivelu, G. Commercial Yeast Extracts Mediated Green Synthesis of Silver Chloride Nanoparticles and Their Anti-Mycobacterial Activity. *Journal of Cluster Science* **2020**, *31*, 287–291, doi:10.1007/s10876-019-01626-4.

53. Faramarzi, S.; Anzabi, Y.; Jafarizadeh-Malmiri, H. Nanobiotechnology Approach in Intracellular Selenium Nanoparticle Synthesis Using *Saccharomyces Cerevisiae*—Fabrication and Characterization. *Archives of Microbiology* **2020**, *202*, 1203–1209, doi:10.1007/s00203-020-01831-0.

54. Mukherjee, P.; Ahmad, A.; Mandal, D.; Senapati, S.; Sainkar, S.R.; Khan, M.I.; Parishcha, R.; Ajaykumar, P. V.; Alam, M.; Kumar, R.; et al. Fungus-Mediated Synthesis of Silver Nanoparticles and Their Immobilization in the Mycelial Matrix: A Novel Biological Approach to Nanoparticle Synthesis. *Nano Letters* **2001**, *1*, 515–519, doi:10.1021/nl0155274.

55. Priyabrata Mukherjee, Satyajyoti Senapati, Deendayal Mandal, Absar Ahmad, M. Islam Khan, RajivKumar, and M.S. Extracellular Synthesis of Gold.Pdf. *Chem Bio Chem.* **2002**, *5*, 461–463.

56. Philip, D. Biosynthesis of Au, Ag and Au-Ag Nanoparticles Using Edible Mushroom Extract. *Spectrochimica Acta - Part A: Molecular and Biomolecular Spectroscopy* **2009**, *73*, 374–381, doi:10.1016/j.saa.2009.02.037.

57. Khan, Z.; Bhadouria, P.; Bisen, P. Nutritional and Therapeutic Potential of Spirulina. *Current Pharmaceutical Biotechnology* **2005**, *6*, 373–379, doi:10.2174/138920105774370607.

58. Senapati, S.; Syed, A.; Moez, S.; Kumar, A.; Ahmad, A. Intracellular Synthesis of Gold Nanoparticles Using Alga *Tetraselmis Kochinensis*. *Materials Letters* **2012**, *79*, 116–118, doi:10.1016/j.matlet.2012.04.009.

59. Roychoudhury, P.; Pal, R. Synthesis and Characterization of Nanosilver-A Blue Green Approach. *Indian Journal of Applied Research* **2011**, *4*, 54–56, doi:10.15373/2249555x/jar2014/17.

60. Sinha, S.N.; Paul, D.; Halder, N.; Sengupta, D.; Patra, S.K. Green Synthesis of Silver Nanoparticles Using Fresh Water Green Alga *Pithophora Oedogonia* (Mont.) Wittrock and Evaluation of Their Antibacterial Activity. *Applied Nanoscience (Switzerland)* **2015**, *5*, 703–709, doi:10.1007/s13204-014-0366-6.

61. Kumar, P.; Senthamil Selvi, S.; Lakshmi Prabha, A.; Prem Kumar, K.; Ganeshkumar, R.S.; Govindaraju, M. Synthesis of Silver Nanoparticles from *Sargassum Tenerimum* and Screening Phytochemicals for Its Antibacterial Activity. *Nano Biomedicine and Engineering* **2012**, *4*, 12–16, doi:10.5101/nbe.v4i1.p12-16.

62. Saravanakumar, K.; Chelliah, R.; Shanmugam, S.; Varukattu, N.B.; Oh, D.H.; Kathiresan, K.; Wang, M.H. Green Synthesis and Characterization of Biologically Active Nanosilver from Seed Extract of *Gardenia Jasminoides* Ellis. *Journal of Photochemistry and Photobiology B: Biology* **2018**, *185*, 126–135, doi:10.1016/j.jphotobiol.2018.05.032.

63. Khatoon, N.; Mazumder, J.A.; Sardar, M. Biotechnological Applications of Green Synthesized Silver Nanoparticles. *Journal of Nanosciences: Current Research* **2017**, *02*, 1–8, doi:10.4172/2572-0813.1000107.

64. Stozhko, N.Y.; Bukharinova, M.A.; Khamzina, E.I.; Tarasov, A. V.; Vidrevich, M.B.; Brainina, K.Z. The Effect of the Antioxidant Activity of Plant Extracts on the Properties of Gold Nanoparticles. *Nanomaterials* **2019**, *9*, 1–16, doi:10.3390/nano9121655.

65. Momeni, S.; Nabipour, I. A Simple Green Synthesis of Palladium Nanoparticles with Sargassum Alga and Their Electrocatalytic Activities Towards Hydrogen Peroxide. *Applied Biochemistry and Biotechnology* **2015**, *176*, 1937–1949, doi:10.1007/s12010-015-1690-3.
66. Kumar, A.; Vemula, P.K.; Ajayan, P.M.; John, G. Silver-Nanoparticle-Embedded Antimicrobial Paints Based on Vegetable Oil. *Nature Materials* **2008**, *7*, 236–241, doi:10.1038/nmat2099.
67. Moulton, M.C.; Braydich-Stolle, L.K.; Nadagouda, M.N.; Kunzelman, S.; Hussain, S.M.; Varma, R.S. Synthesis, Characterization and Biocompatibility of “Green” Synthesized Silver Nanoparticles Using Tea Polyphenols. *Nanoscale* **2010**, *2*, 763–770, doi:10.1039/c0nr00046a.
68. Fardsadegh, B.; Jafarizadeh-Malmiri, H. Aloe Vera Leaf Extract Mediated Green Synthesis of Selenium Nanoparticles and Assessment of Their in Vitro Antimicrobial Activity against Spoilage Fungi and Pathogenic Bacteria Strains. *Green Processing and Synthesis* **2019**, *8*, 399–407, doi:10.1515/gps-2019-0007.
69. Sasidharan, D.; Namitha, T.R.; Johnson, S.P.; Jose, V.; Mathew, P. Synthesis of Silver and Copper Oxide Nanoparticles Using Myristica Fragrans Fruit Extract: Antimicrobial and Catalytic Applications. *Sustainable Chemistry and Pharmacy* **2020**, *16*, 100255, doi:10.1016/j.scp.2020.100255.
70. Gardea-Torresdey, J.L.; Gomez, E.; Peralta-Videa, J.R.; Parsons, J.G.; Troiani, H.; Jose-Yacaman, M. Alfalfa Sprouts: A Natural Source for the Synthesis of Silver Nanoparticles. *Langmuir* **2003**, *19*, 1357–1361, doi:10.1021/la020835i.
71. Marchiol, L.; Mattiello, A.; Pošćić, F.; Giordano, C.; Musetti, R. In Vivo Synthesis of Nanomaterials in Plants: Location of Silver Nanoparticles and Plant Metabolism. *Nanoscale Research Letters* **2014**, *9*, 1–11, doi:10.1186/1556-276X-9-101.

Disclaimer/Publisher’s Note: The statements, opinions, and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of Dasinya Journal and/or the editor(s). Dasinya Journal and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions, or products referred to in the content.